

# DC12-160(12V160Ah)



## Specification

Cells Per Unit	6
Voltage Per Unit	12
Capacity	160Ah@20hr-rate to 1.75V per cell @25°C
Weight	Approx. 48.0 Kg (Tolerance ±3.0%)
Internal Resistance	Approx. 4.5 mΩ
Terminal	F5(M8)/F12(M8)
Max. Discharge Current	1600A (5 sec)
Design Life	12 years (floating charge)
Max. Charging Current	48.0 A
Reference Capacity	C3 122.3AH C5 137.8AH C10 152.4AH C20 160.0AH
Float Charging Voltage	13.6 V~13.8 V @ 25°C Temperature Compensation: -3mV/°C/Cell
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell
Operating Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C ±5°C
Self Discharge	RITAR Valve Regulated Lead Acid (VRLA) batteries can be stored for up to 6 months at 25°C and then recharging is recommended. Monthly Self-discharge ratio is less than 3% at 25°C. Please charged batteries before using.
Container Material	A.B.S. UL94-HB, UL94-V0 Optional.



DC (Deep Cycle) series batteries provide superior high integrity and reliability. It is specially designed for frequent cyclic charge and discharging. By using strong grids, thick plate and specially active material are designed for repeated deep-discharge applications. The DC series batteries offer 30% more cyclic life than the standby series. It is suitable for solar and wind renewable energy storage, mobility and medical equipment and cable TV etc.



ISO 9001



ISO 14001




OHSAS 18001



MH 28539



## Dimensions



### Constant Current Discharge Characteristics : A(25°C)

F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	349.7	280.5	172.5	97.18	57.87	45.08	35.36	30.08	19.29	16.00	8.292
1.65V	322.1	262.4	163.4	93.87	55.93	43.69	34.30	29.13	19.14	15.85	8.248
1.70V	298.5	246.7	154.9	90.86	54.44	41.85	33.24	28.35	18.84	15.54	8.144
1.75V	273.9	231.1	148.8	88.00	52.35	40.77	32.34	27.56	18.53	15.39	8.000
1.80V	249.2	211.6	143.3	84.09	50.56	40.00	31.58	27.20	18.23	15.24	7.923
1.85V	195.0	175.1	121.5	75.06	46.24	37.23	29.62	25.04	17.17	14.32	7.849

### Constant Power Discharge Characteristics : WPC(25°C)


F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	595.4	489.4	313.4	182.4	109.4	85.60	68.15	56.93	37.60	31.38	16.55
1.65V	573.3	475.8	306.1	179.3	106.5	83.46	66.49	55.39	37.30	31.08	16.41
1.70V	535.1	450.4	291.4	174.0	103.8	80.27	64.37	54.01	36.84	30.47	16.26
1.75V	497.9	425.1	281.2	169.2	100.1	78.29	62.86	52.78	36.24	30.17	15.96
1.80V	458.7	393.0	272.1	162.3	97.84	77.85	61.65	52.07	35.64	29.87	15.82
1.85V	363.9	330.1	233.3	145.8	90.09	72.62	58.03	48.16	33.69	28.21	15.67

(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values. The battery must be fully charged before the capacity test. The C<sub>20</sub> should reach 95% after the first cycle and 100% after the third cycle.

# DC12-160(12V160Ah)




## Discharge Characteristics Curve




## Charge Characteristic Curve for Cycle Use(IU)




## Cycle Life in Relation to Depth of Discharge




## Relationship Between Charging Voltage and Temperature




## Temperature Effects on Capacity




## Storage Characteristics



## Effect of Temperature on Long Term Life



## Relationship of OCV And State of Charge(20°C)



(Note) All above information shall be changed without prior notice, Ritar reserves the right to explain and update the latest information.