



EV12-180(12V180Ah)



Specification


Cells Per Unit	6
Voltage Per Unit	12
Capacity	180Ah@10hr-rate to 1.80V per cell @25°C
Weight	Approx. 53.0 Kg (Tolerance ±3.0%)
Internal Resistance	Approx. 4.0 mΩ
Terminal	F12(M8)/F16(M8)
Max. Discharge Current	1800A (5 sec)
Cold Cranking Ampere(CCA)	780A
Maxi. Charging Current	54.0A
Reference Capacity	C3 138.0AH
	C5 157.0AH
	C10 180.0AH
	C20 190.8AH
Float Charging Voltage	13.6 V~13.8 V @ 25°C Temperature Compensation: -3mV/°C/Cell
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell
Operating Temperature Range	Discharge: -20°C~60°C
	Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C ±5°C
Self Discharge	RITAR Valve Regulated Lead Acid (VRLA) batteries can be stored for up to 6 months at 25°C and then recharging is recommended. Monthly Self-discharge ratio is less than 3% at 25°C. Please charged batteries before using.
Container Material	A.B.S. UL94-HB, UL94-V0 Optional.



EV (Electric Vehicle) series is specially designed for frequent discharge deep cycle application. By using the specially designed active material, strong grids and thick plate construction, the EV series battery offers reliable performance in high load situations and could provide competitive cycle performance. It is suitable for Electric Vehicle and Golf cart, Floor Machines, Forklifts, Aerial lifts, Robotics, Marine, RV, Mobility and Medical Equipment, and most outdoor application.



Dimensions



Constant Current Discharge Characteristics : A(25°C)

F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	411.2	326.6	199.0	106.6	64.9	50.3	39.9	34.0	22.8	19.0	9.93
1.65V	388.6	312.2	191.1	103.0	62.9	48.8	38.9	33.1	22.6	18.8	9.78
1.70V	357.7	292.4	182.7	99.6	60.8	47.4	37.8	32.2	22.2	18.5	9.66
1.75V	327.4	272.1	174.6	96.0	58.7	46.0	36.8	31.4	21.9	18.2	9.54
1.80V	296.4	251.3	166.9	92.3	56.6	44.6	35.8	30.6	21.6	18.0	9.44
1.85V	242.2	208.5	143.7	82.8	51.8	41.2	33.3	28.6	20.2	16.9	8.97

Constant Power Discharge Characteristics : WPC(25°C)

F.V/Time	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	699.0	570.9	361.5	200.4	123.1	96.1	76.7	65.5	44.6	37.3	19.6
1.65V	673.2	553.9	350.7	194.6	119.7	93.5	74.9	64.1	44.2	36.9	19.3
1.70V	631.2	526.5	338.6	189.5	116.4	91.4	73.1	62.6	43.6	36.4	19.1
1.75V	588.1	497.1	327.0	183.7	112.9	89.0	71.5	61.2	43.1	36.0	18.9
1.80V	541.7	465.5	315.7	177.7	109.4	86.6	69.7	59.9	42.5	35.6	18.7
1.85V	450.6	391.8	274.6	160.3	100.8	80.4	65.0	56.0	40.0	33.5	17.8


(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values. The battery must be fully charged before the capacity test. The C₁₀ should reach 95% after the first cycle and 100% after the third cycle.




EV12-180(12V180Ah)




Charge Characteristic Curve for Cycle Use(IIUU)




Charge Characteristic Curve For Cycle Use(III)




Cycle Life in Relation to Depth of Discharge




Storage Characteristics




Discharge Characteristics Curve




Relationship Between Charging Voltage and Temperature



Relationship of OCV And State of Charge(20°C)



Temperature Effects on Capacity



(Note) All above information shall be changed without prior notice, Ritar reserves the right to explain and update the latest information.